



PHYSICAL PROPERTIES—TEST DATA	
Adhesion (ASTM D4541, elcometer pull-off)	>2,700 psi (18.61 MPa)
Abrasion Resistance (ASTM D 4060, Tabor Test 1,000 cycles, CS 17 wheel, 1kg)	42 milligrams loss
Direct Impact Resistance (ASTM D 2794)	40 inch-pounds at 25-30 mils
Salt Fog Resistance (ASTM B117) - test ongoing	Over 2,000 hours with no blisters/undercreep
Compressive Strength (ASTM D 695)	14,000 psi (110.2 MPa)
Tensile Strength (ASTM C 307)	6,000 psi (42.8 MPa) - 25-30 mils at 73°F (23°C)
Cathodic Disbondment (NACE RP0394-94)	Disbonded Radius: 5.00 mm avg. at 38.3 mils
Flexibility (NACE RP0394-94)	1% elongation at 37°F (3°C)
VOC (Volatile Organic Compounds)	zero